



US Floors International LLC
Textielstraat 20
8790 WAREGEM

Your notice of
01-10-2020

Your reference

Date
10-11-2020

Analysis Report 20.05971.03

Modification of analysis report 20.05971.02, made on 09-11-2020

Required tests :

EN 13501-1 (2019)

Sample id	Information given by the client	Date of receipt
T2021104	COREtec Sound Core 8 mm (A)	01-10-2020

Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2021104 - COREtec Sound Core 8 mm (A)

Information given by the client

Product standard	EN 13501-1 (2019)
Floor covering type	Loose-laid panels - Semi-rigid multilayer modular floor covering (MMF) panels with wear resistant top layer
EN product standard	EN 16511
FR treated	no
Mass	8.2 kg/m ²
Thickness	8 mm

Notified body No: 0493

Reference: T2021104 - COREtec Sound Core 8 mm (A)

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Date of ending the test 29-10-2020
Standard used EN ISO 11925-2 (2010)
Product standard EN 13501-1 (2019)

Floor covering

Deviation from the standard -

Conditioning 23°C, relative humidity 50%
Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Substrate Fibre cement board - density (1800 ± 200) kg/m³
Mounting Loose-laid

Specimens have not been cleaned

Flame application time (s) 15
Flame application Surface

	Length			Width		
	1	2	3	4	5	6
Time to reach 150 mm mark (s)	*	*	*	*	*	*

* = time to reach the mark > 20 s or mark not reached


Criteria Floorcoverings

time to reach the mark: - > 20 s : Class Efl
- ≤ 20 s : Class Ffl

Classification Class E_n

Limitations

This classification document does not represent type approval or certification of the product.



Reference: T2021104 - COREtec Sound Core 8 mm (A)

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	05-11-2020
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2019)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Fibre cement board - density (1800 ± 200) kg/m ³
Mounting	Loose-laid
Specimens have not been cleaned	
Joint	In length direction : at 25 cm In width direction : at 20.8 cm and each 22.8 cm

Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux * kW/m ²
	10 min	20 min	30 min		
Length					
#1	13	13	13	12 min 00 s	10.8
Width					
#1	15	15	15	12 min 00 s	10.4
#2	13	13	13	12 min 00 s	10.6
#3	13	13	13	12 min 00 s	10.6
Average					10.5

* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2019)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{fl}	E _{fl}	heat flux ≥ 8,0 kW/m ²
C _{fl}	E _{fl}	heat flux ≥ 4,5 kW/m ²
D _{fl}	E _{fl}	heat flux ≥ 3,0 kW/m ²

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Length		
#1	19	103
Width		
#1	22	117
#2	18	90
#3	17	87
Average		98

Additional classification in accordance with EN 13501-1 (2019)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2



Reaction to fire classification : B_n/ s1

*Loose-laid on a non-combustible substrate**

** End use substrates of classes A1 or A2-s1, d0 (EN 13238:2010 § 5.2.2)*

Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of performance by the manufacturer within the context of system 3 of assessment and verification of constancy of performance and CE marking under the Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”